



Product Information

Product Type	Film	PET/PP Antifog
Thickness	42 micron	+/- 5%
Weight	46.6 g/m ²	+/- 5%
Yield	21.5m ²	+/- 5%
Tensile strength @break	MD: 130 N/15 mm TD: 320 N/15mm	=/- 10N/15 mm



Technical Specification

Permeabilities

Oxygen	110 cc/m ² /24hr.bar	ASTM D 3985 23°C and 0% RH
Water Vapour	7.5 g/m ² /24hr	NF H 00-044 38°C and 90% RH
Carbon Dioxide	550 cc/m ² /24hr.bar	ASTM D 3985 23°C and 0% RH

Thermal

Sealing temperature range	95°C to 145°C	n/a
---------------------------	---------------	-----

The above information is made with the best knowledge and conscience. The data are results of experiments conducted in authorized institutes, our own laboratory and from practical knowledge acquired over many years. Due to the numerous and varied application possibilities and the differing packaging methods, it is regretted that a warranty cannot be given.

The packaging manufacture and/or supplier cannot be held responsible for quality changes in the products packed through its reaction with the packaging material or any other factors that may cause such change in quality.

Palletisation

Item	Pieces per Box	Pieces per Pallet	Total Pallet Height (CM)
3906	2	20	160